

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C09D 9/00	A1	(11) International Publication Number: WO 98/53016 (43) International Publication Date: 26 November 1998 (26.11.98)
(21) International Application Number: PCT/US98/10576 (22) International Filing Date: 22 May 1998 (22.05.98) (30) Priority Data: 60/047,529 23 May 1997 (23.05.97) US 60/048,450 3 June 1997 (03.06.97) US (71) Applicant: HUNTSMAN PETROCHEMICAL CORPORATION [US/US]; 7114 North Lamar Boulevard, Austin, TX 78752 (US). (72) Inventors: MARQUIS, Edward, T.; 9004 Collinfield Drive, Austin, TX 78758 (US). BALDWIN, Robert, E.; 802 Parkway, Georgetown, TX 78628 (US). (74) Agent: O'KEEFE, Robert, M.; Jones, O'Keefe & Egan, Building C, Suite 200, 1101 Capital of Texas Highway South, Austin, TX 78746 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: PAINT AND COATING REMOVER (57) Abstract This invention concerns a composition useful as a paint remover, comprising: alkylene carbonate such as propylene carbonate or ethylene carbonate, hydrogen peroxide, and water, and optionally an alcohol such as benzyl alcohol. In another broad respect, this invention concerns a process for removing paint, comprising: applying a composition containing alkylene carbonate, hydrogen peroxide, and water to a painted surface for a time and under conditions effective to cause blistering or bubbling of the paint. In another broad respect, this invention is a composition useful as a paint remover, comprising: dialkyl carbonate, hydrogen peroxide, and water, optionally containing an alcohol, optionally containing a glycol ether. In another broad respect, this invention is a process for removing paint, comprising: applying a composition containing dialkyl carbonate, hydrogen peroxide, and water to a painted surface for a time and under conditions effective to cause blistering or bubbling of the paint.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Larvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

PAINT AND COATING REMOVER

by:

Edward T. Marquis

Robert E. Baldwin

5

BACKGROUND OF INVENTION

This invention relates to compositions for paint and coating removal. More particularly, this invention relates to compositions containing alkylene carbonate or dialkyl carbonate or both, hydrogen peroxide, and water.

10

Paint removing compositions are commonly used in industry, such as for stripping paint from airplane fuselages. Conventional paint remover compositions include methylene chloride, phenol, or caustic. Each of these materials, however, has inherent problems during use. While methylene chloride based compositions are very effective as paint removers, methylene chloride is a highly volatile material which is considered toxic. Similarly, phenol is highly toxic. Furthermore, caustic causes burns and attacks aluminum. Due to the deficiencies and disadvantages of conventional paint removing compositions, new paint removing compositions are highly desirable.

15

SUMMARY OF INVENTION

In one broad respect, this invention is a composition useful as a paint remover, comprising: alkylene carbonate, hydrogen peroxide, and water.

20

In another broad respect, this invention is a process for removing paint, comprising: applying a composition containing alkylene carbonate, hydrogen peroxide, and water to a painted surface for a time and under conditions effective to cause blistering or bubbling of the paint.

25

In another broad respect, this invention is a process for removing paint, comprising: applying a composition containing (a) alkylene carbonate, dialkyl carbonate, or both, (b) hydrogen peroxide, and (c) water to a painted surface for a time and under conditions effective to cause blistering or bubbling of the paint.

In another broad respect, this invention is a composition useful as a paint remover, comprising: dialkyl carbonate, hydrogen peroxide, and water. This composition may optionally contain an alcohol, a glycol ether, an alkylene carbonate, or a combination thereof.

5 In another broad respect, this invention is a process for removing paint, comprising: applying a composition containing dialkyl carbonate, hydrogen peroxide, and water to a painted surface for a time and under conditions effective to cause blistering or bubbling of the paint.

The surfaces to be treated may be sealed with a variety of sealants, such as polysulfide, polyurethane, lacquer, epoxy, and the like. The compositions can be used to
10 remove paints and coatings from furniture, automobiles, boats, trains, airplanes, military vehicles, and so forth.

This invention has a number of advantages. For example, the compositions have several important attributes, including low toxicity, high efficacy in removing paint and coatings, and neutral pH (or slightly acidic or slightly basic pH). Furthermore, in the case of
15 propylene carbonate, the propylene carbonate breaks down into propylene glycol, which is non-toxic. Likewise, hydrogen peroxide decomposes over time to water. Hence, the propylene carbonate compositions of this invention are environmentally friendly, particularly as compared to chlorinated hydrocarbons and the like which are commonly used for paint and coating removing. In addition, the compositions of this invention cause blistering and
20 bubbling in such a short period of time that it is envisioned that the compositions of this invention might be applied in liquid form, as opposed to the gels which are commonly applied which lesson evaporation of the chlorinated hydrocarbons, for example.

It has further been advantageously found that by employing hydrogen peroxide in the form of an at least 50% aqueous solution, a miscible solution forms with alkylene carbonate.
25 In the context of this invention, by miscible solution it is meant a single phase solution. The resulting composition has surprisingly superior paint removing properties, which is believed to be due to the limited amount of water present. The compositions may be blended with additional cosolvents, activators, corrosion inhibitors, and the like, or may be used directly to effect paint removal. The compositions of this invention may advantageously be non-
30 flammable, of low volatility and free of carcinogenic chemicals.

DETAILED DESCRIPTION OF THE INVENTION

The compositions of this invention contain alkylene carbonate or dialkyl carbonate or both, hydrogen peroxide, and water.

The hydrogen peroxide and water can be conveniently obtained from commercial sources as aqueous hydrogen peroxide solutions of varying percentages. Hydrogen peroxide is commonly available in aqueous solutions at a concentration of from about 1 to about 80 percent. For example, industrial solutions are often 30 percent or more by weight hydrogen peroxide solutions. It has been found that in the practice of this invention, the use of a 50% aqueous hydrogen peroxide solution is particularly effective. It may be appreciated that highly concentrated hydrogen peroxide should be handled carefully and appropriately since such materials are considered strong oxidizers. It may also be noted that once the concentrated hydrogen peroxide solution is admixed with carbonate, the concentration of hydrogen peroxide decreases which thus reduces the hazardous nature of the final composition. For example, when the overall concentration of hydrogen peroxide in the admixed composition is less than about 30%, special precautions need not be taken to handle the composition. Use of an aqueous hydrogen peroxide solution having a concentration of from about 30% to about 50% is preferred in the practice of this invention, with a concentration of about 50% providing a superior balance of paint stripping ability and miscibility with carbonate. In this regard, it should be appreciated that a lower hydrogen peroxide concentration of the aqueous solution may require use of cosolvents, surfactants, or the like to provide a miscible final composition.

In one embodiment of this invention, the amount of hydrogen peroxide in the total composition is at least 4 percent by weight. In another embodiment, the amount of hydrogen peroxide in the total composition is at least 10 percent by weight. In another embodiment of this invention, the amount of hydrogen peroxide is at least 15 percent by weight of the total composition or, alternatively, at least 35 percent by weight.

The alkylene carbonate used in the present invention can contain from 2 to 10 carbon atoms. Representative examples of alkylene carbonates that may be employed in the practice of this invention include ethylene carbonate and propylene carbonate. In the practice of this invention, propylene carbonate is preferred.

The dialkyl carbonate used in the present invention may contain from 3 to 25 carbon atoms. The dialkyl carbonate may be of formula $R-CO_2-R'$, wherein R and R' may be the same or different, and may independently in each occurrence be alkyl of from 1 to about 12 carbon atoms. In one embodiment, the dialkyl carbonate may be dimethyl carbonate, diethyl carbonate, or a mixture thereof.

Concentrated solutions would range from about 8 to about 15 percent peroxide with the balance being water and dialkyl carbonate or dialkyl carbonate and alkylene carbonate.

The compositions of this invention may optionally include an alcohol. Representative examples of such alcohols include methanol, ethanol, propanol, butanol, and benzyl alcohol.

In the practice of this invention, benzyl alcohol is preferred. Generally, compositions of this invention contain from 0 to about 90 percent by weight alcohol. For the removal of certain types of coatings, it has been found the efficiency of the carbonate hydrogen deoxidized water solution may be improved by the addition of an alcohol..

In certain embodiments of this invention, the compositions contain from about 10 to about 90 percent by weight alkylene carbonate, from about 0.1 to about 20 percent by weight hydrogen peroxide, and from about 0.1 to about 30 percent water. In certain embodiments of this invention containing alcohol, the compositions contain from about 10 to about 90 percent by weight alkylene carbonate, from about 10 to about 90 percent by weight alcohol, from about 0.1 to about 20 percent by weight hydrogen peroxide, and from about 0.1 to about 30 percent water.

In certain embodiments of this invention, the compositions contain from about 10 to about 90 percent by weight dialkyl carbonate, from about 0.1 to about 20 percent by weight hydrogen peroxide, and from about 0.1 to about 30 percent water. In certain embodiments of this invention, the compositions contain from about 10 to about 90 percent by weight dialkyl carbonate, from about 0 to about 90 percent by weight alcohol, from 0 to about 90 percent by weight glycol ether, from 0 to about 90 percent by weight alkylene carbonate, from about 0.1 to about 20 percent by weight hydrogen peroxide, and from about 0.1 to about 30 percent water.

In addition to the components described above, it is contemplated that the compositions of this invention may optionally contain activators such as formic or oxalic

acid, thickeners, glycol ethers such as propylene glycol methyl ether (PM), dipropylene glycol methyl ether (DPM), or dipropylene glycol n-butyl ether (DPNB), surfactants, acids or bases, stabilizers, corrosion inhibitors, and other additives commonly used in paint removers.

Non-limiting examples of representative thickeners include cellulose ethers such
5 hydroxypropyl cellulose, ethyl cellulose, ethyl hydroxyethyl cellulose, methyl cellulose, and
other alkyl or hydrox alkyl cellulose; silica including colloidal silica; clays such as bentonite
and montmorillonite starch; alumina including colloidal alumina; gum arabic; tragacanth;
agar; sugar derivatives; high molecular weight polyethylene oxides; guar gum; xanthan gum;
polyvinyl pyrrolidone and methyl vinyl ether/maleic anhydride copolymers. It has been
10 found that certain hydroxy alkyl cellulose ethers and certain experimental polymers are
particularly effective and resistant to breakdown in the practice of this invention. Such
cellulose ethers are available commercially from The Dow Chemical Company under the
tradename Methocal® F4MPRG and Dow's Experimental Polymer SCS 41067.06. When a
thickener is used, the amount of such thickener can vary depending on the desired level of
15 thickening for the given application. In general, the amount of thickener employed is about 1
to about 4 percent by weight.

Non-limiting examples of representative corrosion inhibitors include ethoxylated
butynediol, petroleum sulfonates, blends of propargyl alcohol and thiourea. If used, the
amount of such corrosion inhibitors is typically up to about 10% by weight of the total
20 composition.

Chelating agents may also be added to the composition of this invention to complex
with metal ions which may cause degradation of the peroxide. When used, chelating agents
may be used in an amount up to about 10% by weight of the total composition.
Representative examples of such chelating agents include, but are not limited to, ethylene
25 diamine tetraacetic acid (EDTA) and its metal salts, diethylene triamine pentaacetic acid,
polyphosphates, diketones, hydroxy carboxylic acids and phosphonic acids, and the like.

Non-limiting examples of representative stabilizers for hydrogen peroxide which may
be included in the compositions of this invention include C₁₋₄ alkyl anilines, aromatic sulfonic
acids, sulfamic acids, sulfones, sulfoxides, sulfolenes, sulfolanes, amino aryl sulfonic acid,
30 benzene disulfonic acid, p-tolyl sulfonic acid, sulfanilic acid, propylene glycol, glycolic acid,

glycerine, propionic acid, benzoic acid, cis-4-butenediol, and the like and mixtures thereof. The amount of such stabilizers may vary widely when used, and may be used in an amount typically up to about 10% by weight, preferably up to about 1%, of the total composition.

Non-limiting examples of representative surfactants which may optionally be used in the practice of this invention include non-ionic, anionic, cationic and amphoteric surfactants, such as monocarboxyl cocoimidoazoline, higher alkyl sulfate sodium salts, tridecyloxy poly(alkyleneoxy ethanol), ethoxylated or propoxylated alkyl phenol, alkyl sulfoamides, C10-18 alkaryl sulfonates such as alkylbenzene sulfonates, cocoamphadipropionate, cetylpalmitic alkanol amides, hydrogenated castor oil, isooctylphenyl polyethoxy ethanol, sorbitan monopalmitate, C8-18 alkyl pyrrolidone, cocoaminopropionic acid and polyethoxy amino salts thereof. When used, the amount of surfactant should be sufficient to render the composition miscible. Typically the amount of surfactant is from about 0.1 to about 10 percent by weight of the total composition.

The compositions of this invention may also optionally contain a wide variety of other organic cosolvents. Likewise, the present invention may be practiced in the absence of one or more of such solvents. Non-limiting examples of representative classes of such other cosolvents include hydrocarbons, glycols, glycol ethers, glycol ether esters, ethers, esters, phenols, glycols, sulfur-based solvents, chlorinated hydrocarbons, aromatic hydrocarbons nitrated hydrocarbons, amides, and ketones. Such cosolvents may be polar or non-polar, may be protic or aprotic, may be cyclic, branched, or straight-chain, and may contain one or more functional groups. Representative examples of common hydrocarbon solvents include hexane, toluene, xylene, and mixtures of aliphatic and aromatic hydrocarbons. Representative examples of common ether solvents include dibutyl ether, ethyl ether, and diphenyl ether. Representative examples of common ester solvents and lactones include material such as butyrolactone, ethyl acetate, butyl acetate, DBE (dibasic ester mixture from DuPont). Representative examples of common phenols include phenol and the Cresols and resorinols. Representative examples of common glycol solvents include ethylene, propylene and butylene glycols as well as methyl propane diol. Representative examples of common sulfur-based solvents include dimethylsulfoxide (DMSO) and sulfolane. Representative examples of common chlorinated hydrocarbon solvents include methylene chloride, methyl

chloroform, chlorobenzenes and dichlorobenzenes. Representative examples of common nitrated hydrocarbon solvents include nitroethane and nitropropane. Representative examples of common amide solvents include formamide, dimethyl formamide, acetamide, and dimethylacetamide. Representative examples of common ketone solvents include acetone, methyl ethyl ketone (MEK), and methyl isobutyl ketone and methyl isoamylbutone.

When a given composition containing dialkyl carbonate does not form a miscible composition, a co-solvent may be used to provide a miscible composition. For instance, a glycol ether may be added as a co-solvent in an amount effective to solubilize the components of the mixture. Such glycol ethers may be included for other purposes as well. Such amounts may vary depending on the specific composition of interest, as one of skill in the art may appreciate. The particular type and amount of glycol ether which will afford a miscible composition may be identified by routine experimentation. Typically, the amount of glycol ether employed is less than about 90 percent by weight, and more typically from about 10 percent to about 50 percent. Also, an alcohol or alkylene carbonate may be beneficially employed as a co-solvent to provide miscible dialkyl carbonate compositions of this invention.

The conditions under which the paint stripping process of this invention may be practiced may vary. Typically, the process will be conducted under ambient atmospheric conditions. Temperatures from 0°F to about 125°F, although higher temperatures may be used. The paint remover composition may be applied by any convenient method such as by dipping, spraying, or brushing the composition onto the paint surface. For resistant painted surfaces it may be desirable to apply the composition two or more times to fully separate the paint from the surface. It may be desirable to use a rag, scraper, sand blaster, or the like to fully remove paint chips from the surface after the paint remover composition has been given time to fully act. Alternatively, high pressure water spray may be employed to remove paint chips and residual paint remover composition. It may be appreciated that the time required for the paint remover composition to act will vary due to a variety of factors such as temperature, paint type, and particular paint remover formulation being used. In general, application times are between one minute and one hour, although longer application times may be used.

In the practice of this invention, it is contemplated that a thickener may be admixed into a stripping composition just prior to use. This is particularly desirable if thickeners are employed which are not stable in the hydrogen peroxide compositions for extended periods of time. Admixing may be effected by standard techniques, such as stirring agitation, and rolling. The particular mixing method must be tailored to the specific system being thickened. Likewise, the order or rate of addition of thickener and any other additives or components must be tailored to the specific solvent combination involved.

The following examples are illustrative of this invention and are not intended to be limit the scope of the invention or claims hereto. Unless otherwise denoted all percentages are by weight. In the tables, "N/A" denotes "not available."

Example 1: Propylene Carbonate Composition

Various compositions were prepared containing propylene carbonate, as indicated in Table 1. In Table 1, the values for benzyl alcohol, propylene carbonate, formic acid, hydrogen peroxide, and water are based on weight percentages. The benzyl alcohol is an optionally included co-solvent. The hydrogen peroxide was delivered from a 30% aqueous solution. The compositions were applied to a standard aluminum panel having paint and coatings for military use (obtained from Scientific Material International, Inc. of Miami, Florida, Lot 96046-A2 4" x 5", MIL-P-2337 primer, MIL-S-81733 Type 3 polysulfide sealant, MIL-C-83286), and allowed to sit on the panels. The propylene carbonate/hydrogen peroxide/water compositions was surprisingly effective in removing the paint and coatings. In Table 1, the runs in which hydrogen peroxide or propylene carbonate are lacking are not representative of the invention, and are presented for purposes of comparison only. Bubbling and blistering were observed by visual inspection.

The compositions have several important attributes, including low toxicity, high efficacy in removing paint and coatings, and neutral pH (or slightly acidic or slightly basic pH). Furthermore, propylene carbonate breaks down into propylene glycol, which is non-toxic, and hydrogen peroxide decomposes to water. Hence, the propylene carbonate compositions of this invention are environmentally friendly, particularly as compared to chlorinated hydrocarbons and the like which are commonly used for paint and coating removing. In addition, the compositions of this invention cause blistering and bubbling in

such a short period of time that it is envisioned that the compositions of this invention can be applied in liquid form, as opposed to the gels which are commonly applied which lesson evaporation of the chlorinated hydrocarbons, for example. However, on difficult to remove coatings on vertical surfaces, thickeners such as Klucel H (Hercules, Aqualon Division), Dow's Methocell® F4MPRG or Dow's experimental polymer XCS 41067.06 may be required to obtain effective coating removal.

Table 1

Benzyl Alcohol	Propylene Carbonate	Formic Acid	Hydrogen peroxide	Water	Minutes to Blister	Minutes to Bubble
60	40	0	0	0	720*	N/A
58.2	38.8	3	0	0	N/A	360*
56.4	37.6	6	0	0	N/A	345*
	80	0	6	14	24	64
54	36	0	3	7	32	44
48	32	0	6	14	20	35
40	40	0	6	14	20	28
30	50	0	6	14	25	33
20	60	0	6	14	31	38
80	0	0	6	14	Immiscible, 2 phases*	

The "*" denotes experiments that are not representative of this invention, and are presented for comparison only.

Example 2: Ethylene Carbonate Composition

Various compositions were prepared containing ethylene carbonate, as indicated in Table 2. In Table 2, the values for benzyl alcohol, ethylene carbonate, formic acid, hydrogen peroxide, and water are based on weight percentages. As in Example 1, the compositions were applied to a standard panel having paint and coatings for military use (obtained from Scientific Material International, Inc., Lot 96046-A2 4" x 5", MIL-P-2337 primer, MIL-S-81733 Type 3 polysulfide sealant, MIL-C-83286). The ethylene carbonate/benzyl alcohol/hydrogen peroxide/water compositions were surprisingly effective in removing the paint and coatings. In Table 2, the runs in which hydrogen peroxide or ethylene carbonate are lacking are not representative of the invention, and are presented for purposes of comparison only.

The compositions have several important attributes, including low toxicity, high efficacy in removing paint and coatings, and neutral pH (or slightly acidic or slightly basic pH). In addition, the compositions of this invention cause blistering and bubbling in such a short period of time that it is envisioned that the compositions of this invention can be applied in liquid form, as opposed to the gels which are commonly applied which lesson evaporation of the chlorinated hydrocarbons, for example. However, on difficult to remove coatings on vertical surfaces, thickeners such as Klucel H (Hercules, Aqualon Division) or Dow's Methocal® F4MPRG or Dow's experimental polymer XCS 41067.006 may be required to obtain effective coating removal.

Table 2

Benzyl Alcohol	Ethylene Carbonate	Formic Acid	Hydrogen peroxide	Water	Minutes to Blister	Minutes to Bubble
60	40	0	0	0	>150*	N/A
58.2	38.8	3	0	0	100*	>150*
56.4	37.6	6	0	0	41*	>150*
54	36	0	3	7	30	36
45	45	0	3	7	33	40
48	32	0	6	14	20	30
40	40	0	6	14	25	35
42	28	0	9	21	20	32
35	35	0	9	21	20	35

The "*" denotes experiments that are not representative of this invention, and are presented for comparison only.

Example 3: Dialkyl Carbonate Compositions

Various compositions were prepared containing the dialkyl carbonates dimethyl carbonate (DMC) and diethyl carbonate (DEC), as indicated in Table 3. In Table 3, the values for benzyl alcohol (BA), propylene carbonate (PC), propylene glycol n-butyl ether (PNB), and dipropylene glycol n-butyl ether (DPNB) are based on weight percentages. For some of the compositions in Table 3 denoted with a "†" in the Miscible column, a glycol ether was needed to form a miscible composition. As in Example 1, the compositions were

applied to a standard panel having paint and coatings for military use (obtained from Scientific Material International, Inc., Lot 96046-A2 4" x 5", MIL-P-2337 primer, MIL-S-81733 Type 3 polysulfide sealant, MIL-C-83286). The dialkyl carbonate compositions were surprisingly effective in removing the paint and coatings. In Table 3, the runs in which the composition was not miscible are not representative of the invention, and are presented for purposes of comparison only.

The compositions have several important attributes, including low toxicity, high efficacy in removing paint and coatings, and neutral pH (or slightly acidic or slightly basic pH). In addition, the compositions of this invention cause blistering and bubbling in such a short period of time that it is envisioned that the compositions of this invention can be applied in liquid form, as opposed to the gels which are commonly applied which lesson evaporation of the chlorinated hydrocarbons, for example. However, on difficult to remove coatings on vertical surfaces, thickeners such as Klucel H (Hercules, Aqualon Division) or Dow's Methocal® F4MPRG or Dow's Experimental polymer XCS 41067.06 may be required to obtain effective coating removal.

Table 3

DMC	DEC	PC	BA	PNB	DPNB	H ₂ O ₂	Water	Miscible	Minutes to Blister	Minutes to Bubble
61.5	0	0	0	23.1	0	4.6	10.8	Yes [†]	20	30
0	53.3	0	0	0	33.3	4.0	9.3	No*	N/A	N/A
60	0	20	0	0	0	6.0	14.0	Yes	20	30
40	0	40	0	0	0	6.0	14.0	Yes	30	42
20	0	60	0	0	0	6.0	14.0	Yes	55	60
0	40.0	13.3	0	0	33.3	4.0	9.3	No*	N/A	N/A
0	27.6	27.6	0	0	31.0	4.1	9.6	Yes [†]	50	60
0	17.4	52.2	0	0	13.0	5.2	12.2	Yes [†]	40	45
50.0	0	0	16.7	16.7	0	5.0	11.6	Yes [†]	20	30
33.3	0	0	33.3	16.7	0	5.0	11.7	Yes [†]	25	30
16.0	0	0	48.0	20.0	0	4.8	11.2	Yes [†]	20	40
0	40.0	0	13.3	0	33.3	4.0	9.3	No*	N/A	N/A
0	26.7	0	26.7	0	33.3	4.0	9.3	No*	N/A	N/A
0	13.3	0	40.0	0	33.3	4.0	9.3	Yes [†]	35	55
30	0	30	20	0	0	6	14	Yes	20	40
20	0	20	40	0	0	6	14	Yes	25	40
8.3	0	8.3	50.0	16.7	0	5.0	11.7	Yes [†]	30	45
0	20.0	20.0	13.3	0	33.3	4.0	9.3	Yes [†]	45	60
0	13.3	13.3	26.7	0	33.3	4.0	9.3	Yes [†]	49	60
0	6.7	6.7	40.0	0	33.3	4.0	9.3	Yes [†]	49	60

The "*" denotes experiments that are not representative of this invention, and are presented for comparison only.

Example 4: Stability of Propylene Carbonate Compositions

A number of compositions were prepared containing propylene carbonate (PC), water, hydrogen peroxide (H_2O_2), and varying amounts of stabilizer. The compositions were then placed in containers and periodically monitored to determine H_2O_2 content. The results are reported in Table 4.

Table 4

Composi- tion	Weight % of Compounds in Original Solution					H_2O_2 Concentration					
	PC	Stabilizer	Amt Of Stabilizer	H_2O_2	H_2O	2 wks	4 wks	6 wks	8 wks	10 wks	12 wks
4-A 1	57.	None	--	15.0	27.9	14.9	14.7	14.4	14.7	13.9	14.6
4-B 5	61.	Benzoic Acid	0.1	13.4	25.0		13.5		13.2	13.1	13.1
4-C 1	57.	Benzoic Acid	0.1	15.0	27.8	15.0	14.8	14.7	13.6	14.2	14.7
4-D 1	57.	Benzoic Acid	0.05	15.0	27.8	14.9	14.8	14.7	14.9	14.0	14.7
4-E 1	57.	Benzoic Acid	0.01	15.0	27.9	14.8	14.8	14.7	14.5	12.8	14.6
4-F 1	57.	DeQuest ™ 2010	0.1	15.0	27.8	14.9	14.9	15.0	14.7	14.4	14.9
4-G 1	57.	DeQuest ™ 2010	0.05	15.0	27.8	14.9	14.9	14.7	14.1	14.6	12.6
4-H 1	57.	DeQuest ™ 2010	0.01	15.0	27.9	14.9	15.0	14.8	14.8	14.2	14.6

The data in Table 4 shows that, surprisingly, carbonate/water/ H_2O_2 compositions are stable. Thus, the hydrogen peroxide does not decrease in amount to any appreciable degree over a 12 week span. Furthermore, it was found that, unexpectedly, the compositions were single phase despite high H_2O loadings of 25 percent or more. This is particularly notable because water

4, phase separation occurs in the absence of hydrogen peroxide. While not wishing to be bound by theory, it is contemplated that the hydrogen peroxide functions as a coupler to provide a single phase solution. The data in Table 4 also appears to suggest that use of a stabilizer is not particularly important to maintain a stable composition and, as such, is optionally employed in the practice of this invention. It is thus notable that compositions having 15 percent or more peroxide are stable.

The fluctuations in concentration in Table 4 (i.e., an increase in peroxide) are attributable to normal experimental error.

Example 5: Thickened Compositions

10 A number of carbonate compositions were prepared by mixing components with stirring. Various thickeners were included in the compositions. The compositions are described in Table 5-A. In Table 5-A, "a" denotes methyl cellulose (Dow Chemical's Methocell™ 311), "b" denotes hydroxy propyl cellulose (Klucel™ H cellulose from Aqualon), and "c" denotes hydroxy propyl methyl cellulose (Methocell™ F4MPRG by Dow
15 Chemical).

Table 5-A

Composition	Weight % of Components				
	Benzyl Alcohol	PC	H ₂ O ₂	H ₂ O	Thickener
5-A	48.0	32.0	6.3	11.7	2.0b
5-B	46.60	31.00	7.00	13.00	2.40b
5-C	45.60	30.40	7.00	13.00	4.00b
5-D	46.32	30.88	7.00	13.00	2.80a
5-E	46.46	30.97	7.09	13.18	2.30a
5-F	46.32	30.88	7.00	13.00	2.80c
5-G	46.46	30.97	7.09	13.18	2.30c
5-H	46.46	30.97	7.09	13.18	2.30b
5-I	46.32	30.88	7.00	13.00	2.80b
5-J	46.6	31.1	7.0	13.0	2.3b
5-K	46.5	31.0	7.0	13.0	2.5b
5-L	46.4	30.9	7.0	13.0	2.7b
5-M	46.3	30.8	7.0	13.0	2.9b
5-N	46.6	31.1	7.0	13.0	2.3c
5-O	46.5	31.0	7.0	13.0	2.5c
5-P	46.4	30.9	7.0	13.0	2.7c
5-Q	46.3	30.8	7.0	13.0	2.9c
5-R	46.7	31.2	7.0	13.0	2.1b
5-S	46.9	31.2	7.0	13.0	1.9b
5-T	47.0	31.3	7.0	13.0	1.7b
5-U	47.1	31.4	7.0	13.0	1.5b

All of compositions 5-A through 5-U were single phase. The compositions were then placed in closed vessels and monitored for both viscosity stability and H₂O₂ stability. The results of these tests are shown in Table 5-B. "N/A" denotes that no data was collected for the given entry.

Table 5-B

Compo- sition	R m Temperature Viscosity cps						H2O2 Concentration, Weight %					
	2 wks	4 wks	8 wks	12- 14 wks	16 wks	20- 21 wks	2 wks	4 wks	8 wks	12- 14 wks	16 wks	20- 21 wks
5-A	N/A	N/A	2560	1930	2260	1740	6.2	6.3	6.2	6.2	5.9	5.9
5-B	3720	2740	2860	1960	1610	N/A	6.6	7.1	7.0	6.8	6.8	N/A
5-C	18000	12160	9440	5200	4380	N/A	7.2	6.9	7.1	7.0	7.0	N/A
5-D	416	97	N/A	96	64	N/A	6.3	6.5	6.4	6.4	5.9	N/A
5-E	220	55	N/A	78	58	N/A	6.6	6.6	6.4	6.3	6.3	N/A
5-F	40400	21280	16080	13300	8640	N/A	7.0	6.9	6.4	6.8	6.8	N/A
5-G	17120	13900	8400	4500	4400	N/A	5.5	6.7	7.0	6.7	6.8	N/A
5-H	4880	5080	4520	2800	3280	N/A	7.1	7.1	6.5	6.5	6.9	N/A
5-I	8320	7640	7680	6760	6400	N/A	7.1	7.1	7.1	7.1	7.0	N/A
5-J	1380	1155	972	N/A	N/A	N/A	6.0	7.0	6.2	N/A	N/A	N/A
5-K	1090	528	272	N/A	N/A	N/A	6.8	6.7	2.4	N/A	N/A	N/A
5-L	59	32	23	N/A	N/A	N/A	6.0	5.8	5.5	N/A	N/A	N/A
5-M	24	20	15	N/A	N/A	N/A	5.2	4.3	3.9	N/A	N/A	N/A
5-N	15600	4280	2280	N/A	N/A	N/A	7.0	7.1	6.5	N/A	N/A	N/A
5-O	2100	432	221	N/A	N/A	N/A	6.7	6.2	6.3	N/A	N/A	N/A
5-P	6400	1380	650	N/A	N/A	N/A	6.9	6.8	6.5	N/A	N/A	N/A
5-Q	46400	19000	11500	N/A	N/A	N/A	6.6	6.7	6.9	N/A	N/A	N/A
5-R	28	N/A	27.2	N/A	N/A	N/A	6.1	N/A	5.7	N/A	N/A	N/A
5-S	16	N/A	18.4	N/A	N/A	N/A	5.6	N/A	5.0	N/A	N/A	N/A
5-T	29	N/A	24.7	N/A	N/A	N/A	6.3	N/A	5.9	N/A	N/A	N/A
5-U	33	N/A	26.8	N/A	N/A	N/A	6.6	N/A	6.2	N/A	N/A	N/A

The data in Table 5-B shows that the compositions of this invention that optionally contain a thickener are stable. It can be seen that efficacy of the thickener may vary depending on type of thickening agent. It can also be seen that in some instances (i.e., 5-R through 5-U) that the amount of thickening agent needed to effect thickening will vary. Since in general viscosity decreases over time, in some instances it may be preferable to add the thickener immediately preceding application to a surface to be treaded.

WHAT IS CLAIMED IS:

1. A composition useful as a paint remover, comprising: alkylene carbonate, hydrogen peroxide, and water.
- 5 2. The composition of claim 1, wherein the alkylene carbonate is propylene carbonate or ethylene carbonate.
3. The composition of claim 1, wherein the alkylene carbonate is propylene carbonate.
- 10 4. The composition of claim 1, further comprising an alcohol.
5. The composition of claim 1, wherein the composition contains from about 10 to about 90 percent by weight alkylene carbonate, from about 0.1 to about 20 percent by weight hydrogen peroxide, and from about 0.1 to about 30 percent water.
- 15 6. The composition of claim 1, further comprising a thickener.
7. The composition of claim 1, further comprising a thickener, wherein the thickener is a cellulose thickener and is present in an amount up to about 10 percent by weight of the
20 composition.
8. The composition of claim 1 in the absence of an ester.
9. The composition of claim 1 further comprising an organic cosolvent.
- 25 10. The composition of claim 1 wherein the hydrogen peroxide is present in an amount of at least about 4 percent by weight.
11. The composition of claim 1 wherein the hydrogen peroxide is present in an amount of
30 at least about 10 percent by weight.

12. The composition of claim 1 wherein the hydrogen peroxide is present in an amount of at least about 10 percent.
- 5 13. The composition of claim 1 where the alkylene carbonate is present in an amount of at least about 40 percent by weight of the total composition.
14. The composition of claim 1 wherein the hydrogen peroxide is present in an amount of at least about 35 percent by weight of the total composition.
- 10 15. The composition of claim 1 wherein the composition is free of formic acid.
16. The composition of claim 1 in the absence of an ester.
- 15 17. A composition consisting essentially of at least about 10 by weight propylene carbonate, from about 10 to about 90 percent by weight benzyl alcohol, from about 0.1 to about 20 percent by weight hydrogen peroxide, and from about 0.1 to about 30 percent water.
18. A process for removing paint, comprising: applying a composition containing
20 alkylene carbonate, hydrogen peroxide, and water to a painted surface for a time and under conditions effective to cause blistering or bubbling of the paint.
19. The process of claim 18, wherein the composition includes an alcohol.
- 25 20. The process of claim 18, wherein the alkylene carbonate is propylene carbonate.
21. A composition useful as a paint remover, comprising: dialkyl carbonate, hydrogen peroxide, and water.

22. The composition of claim 21, wherein the dialkyl carbonate is dimethyl carbonate, diethyl carbonate, or mixtures thereof.
23. The composition of claim 21 in the form of a miscible solution.
- 5 24. The composition of claim 21, further comprising a glycol ether.
25. The composition of any of claims 21, wherein the composition contains from about 10 to about 90 percent by weight dialkyl carbonate, from about 0.1 to about 20 percent by weight
10 hydrogen peroxide, and from about 0.1 to about 30 percent water.
26. A miscible composition useful as a paint remover, comprising: from about 10 to about 90 percent by weight dimethyl carbonate or diethyl carbonate, from about 0 to about 90 percent by weight benzyl alcohol, from 0 to about 90 percent by weight glycol ether, from 0
15 to about 90 percent by weight alkylene carbonate, from about 0.1 to about 20 percent by weight hydrogen peroxide, and from about 0.1 to about 30 percent water.
27. A process for removing paint, comprising: applying a composition containing dialkyl carbonate, hydrogen peroxide, and water to a painted surface for a time and under conditions
20 effective to cause the paint to separate from the surface.
28. The process of claim 27, wherein the dialkyl carbonate is dimethyl carbonate, diethyl carbonate, or mixtures thereof.
- 25 29. The process of claim 27 wherein the composition is in the form of a miscible solution.
30. The process of claim 27, wherein the composition further comprises a glycol ether.

31. The process of claim 27, wherein the composition contains from about 10 to about 90 percent by weight dialkyl carbonate, from about 0.1 to about 20 percent by weight hydrogen peroxide, and from about 0.1 to about 30 percent water.
- 5 32. The process of claim 27 wherein the composition is a miscible composition comprising: from about 10 to about 90 percent by weight dimethyl carbonate or diethyl carbonate, from about 0 to about 90 percent by weight benzyl alcohol, from 0 to about 90 percent by weight glycol ether, from about 0.1 to about 20 percent by weight hydrogen peroxide, and from about 0.1 to about 30 percent water.
- 10 33. A composition useful as a paint remover, comprising a miscible mixture of propylene carbonate and an aqueous hydrogen peroxide solution, wherein the concentration of hydrogen peroxide in the solution is about 10 to about 50 percent by weight.
- 15 34. The composition of claim 33 in the absence of an ester.
35. A composition useful as a paint remover, consisting of a miscible mixture of propylene carbonate and an aqueous hydrogen peroxide solution
- 20 36. A process for the production of a paint remover composition, comprising: combining (a) alkylene carbonate, dialkyl carbonate, or both and (b) an aqueous hydrogen peroxide solution to form the composition.
37. A process for removing a coating from a surface, comprising:
- 25 providing a miscible composition of alkylene carbonate, hydrogen peroxide, and water;
- adding a thickening agent to the miscible composition and mixing the resulting composition to form a thickened composition;

applying the thickened composition to a coated surface for a time sufficient and under conditions effective to separate at least a portion of the coating from the surface; and

removing the coating and thickened composition from the surface.

5

38. The process of claim 37 wherein the coating is paint.

39. The process of claim 37 wherein the alkylene carbonate is propylene carbonate.

10 40. The process of claim 37 wherein the thickened composition contains about 10 to about 90 percent by weight propylene carbonate, about 0.1 to about 20 percent by weight hydrogen peroxide, and about 0.1 to about 30 percent water.

41. The process of claim 40 wherein the coating is paint.

15

42. The process of claim 41 wherein the surface is aluminum.

INTERNATIONAL SEARCH REPORT

In. ational Application No

PCT/US 98/10576

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C09D9/00

According to International Patent Classification(IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 215 675 A (GEOFFREY J. WILKINS) 1 June 1993 see column 2, line 28-33 see column 4, line 27-30 see column 5, line 37-46; table I	1-13, 15, 16, 18-20, 35-42
P, X	WO 97 29158 A (DASIC INTERNATIONAL) 14 August 1997 see abstract page 2, last paragraph see page 3, paragraph 1 see page 4, line 7-10 see page 4, paragraph 3	1, 2, 4-8, 10-12, 14-16, 18, 19, 36-38

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

27 August 1998

Date of mailing of the international search report

04/09/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Girard, Y

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/10576

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5215675 A	01-06-1993	AU 3598793 A	21-10-1993
		CA 2130178 A	30-09-1993
		WO 9318865 A	30-09-1993
WO 9729158 A	14-08-1997	AU 1613797 A	28-08-1997